



Changzhou Sanzhong Welding Materials Co.,Ltd

www.asweld.com

Standard: AWS A 5.9 YB/T5092	Chemical Composition %								
	C	Mn	Si	Cr	Ni	P	S	Mo	Cu
Grade ER309LSi	≤0.03	1.0 – 2.5	0.65 – 1.0	23 – 25	12 – 14	≤0.03	≤0.03	≤0.75	≤0.75
Type	Spool (MIG)				Tube (TIG)				
Specification (MM)	0.8、0.9、1.0、1.2、1.6、2.0				1.6、2.0、2.4、3.2、4.0、5.0				
Package	S100/1kg S200/5kg S270,S300/15kg-20kg				5kg/box	10kg/box	length :1000MM		
Mechanical Properties	Tensile Strength Mpa				Elongation after fracture A (%)				
	≥ 550				≥ 35				
Diameter (MM)	0.8	1.0	1.2	1.6	2.0	2.5	3.2		
Current (A)	70 ~ 150	100 ~ 200	140 ~ 220	50 ~ 100	100 ~ 200	200 ~ 300	300 ~ 400		
Application	<p>ER309LSi, also known as H03Cr24Ni13Si1, is mainly composed of ultra-low C-23Cr-13Ni. It is a stainless steel MIG wire, which can be welded in all position. Good fluidity of molten iron, thus more beautiful shape, smooth wire feeding, stable arc, few spatter, because of low carbon content, good corrosion resistance.</p> <p>It is often used in welding carbon steel and stainless steel, surfacing transition metal on the inner wall of reaction vessel in petrochemical industry, or in martensite and ferrite stainless steel with poor toughness.</p>								
Notice	<ol style="list-style-type: none"> 1. Oil, dirt and rust on the welding wire surface should be removed before welding. Surface impurities such as oil, rust and water should be thoroughly removed in the welding place, so as to prevent blowhole, crack and so on during welding. The surface of the groove and its surroundings should be polished with metallic gloss. 2. In order to obtain good mechanical properties of welding seam, suggest protect gas Ar+2%O2 and shield gas flow rate 20-25 L/min for MIG welding. For TIG welding, suggest protect gas pure Ar and shield gas flow rate 8-15 L/min, Arc length 1~3 mm; Length of the tungsten pole is about 3~5 mm; wind speed limit ≤ 1.0 m/s, argon protection at the back of welding area. 3. In the welding process, the welding line energy directly affects the mechanical properties and crack resistance of weld metal, and should be paid more attention to. 4. The above welding methods, conditions and specifications are for reference only. Users should evaluate the welding process according to their own welding characteristics before using the welding wire for the formal product welding. 								



TEL:86 189 1234 9999

E-mail: manager@kkweld.com

Whatsapp : +86 189 1234 9999